



Shenzhen BST Technology Co., Ltd.



中国认可
国际互认
检测
TESTING
CNAS L3574

UN38.3 Test Report

SLAUMXLI36-24

**Sample Name
& Model**

Lithium Battery 24V 36Ah

Ultramax Batteries Limited

Consignor

Ultramax Batteries Limited



Shenzhen BST Technology Co., Ltd.



Shenzhen BST Technology Co., Ltd.

Sample Name	Lithium Battery		Sample Model	24V 36Ah	
Consignor	Ultramax Batteries Limited				
Address	Watkins House,Pegamoid Rd.,London N18 2NG				
Manufacturer	Ultramax Batteries Limited				
Address	Watkins House,Pegamoid Rd.,London N18 2NG				
Manufacturer Of Cell	Ultramax Batteries Limited				
Use	--				
	Lithium Battery		Composing Mode	8S6P	
Normal Voltage	25.6V	Rated Capacity	36Ah	Limited Charge Voltage	28.8V
Watt-hour	921.6 Wh	Form	Almost Cuboid	Charging Cut-off Voltage	29.2V
Charge Current	7.2A	Max Continuous Charge Current	30A	End Charge Current	--
Discharge Cut-off Voltage	20.0V	Max. Continuous Discharge Current	50A	Cell Rated Capacity	6Ah
Cells Number	48	Cell Model	32700	Trademark	--
Test method and criterion	ST/SG/AC.10/11/Rev.6/Amend.1 38.3 UNITED NATIONS “ Recommendations in the TRANSPORT OF DANGEROUS GOODS” Manual of Tests and Criteria S T/SG/AC.10/11/Rev.6/Amend.1 38.3				
Accepted date	2022-04-16		Test date	2022-04-16~2022-05-11	
Test items	Altitude simulation, Thermal test, Vibration, Shock, External short circuit, Impact, Overcharge, Forced discharge.				



Shenzhen BST Technology Co., Ltd.

Item		Samples Number			
Altitude simulation		Z1~Z2 X1~X2			
Thermal test					
Vibration					
Shock					
External Short Circuit					
Crush		Z3~Z7 X3~X7			
Overcharge		Z8~Z9 X8~X9			
Forced discharge		Z10~Z19 X10~X19			
Conclusion	The sample has passed the test items of UNITED NATIONS “Recommendations in the TRANSPORT OF DANGEROUS GOODS” Manual of Tests and Criteria ST/SG/AC.10/11/Rev.6/Amend.1 38.3. <div>检测专用章</div> (Issue date): 2022-05-11				
Compiler:	文军	Checker:	张海洋	Approver:	严志明



Sample No	Description of the sample
Z1~Z2, Z3~Z7	Batteries at first cycle in fully charged states;
X1~X2, X3~X7	Batteries after 25 cycles ending in fully charged states;
Z8~Z9	Cells at first cycle at 50% of the design rated capacity;
X8~X9	The 25th cycle of charging and discharging 50% of the battery cell in rated capacity state;
Z10~Z19	Cells at first cycle in fully discharged states;
X10~X19	Cells after 25 cycles ending in fully discharge states.
Test case verdicts: Test case does not apply to the test object----- N/A(Not applicable) Test item does meet the requirement----- P(ass) Test item does not meet the requirement----- F(ail)	

----- Test Method And Verdict-----

Clause	Requirements	Result	Verdict
38.3.4.1	Test 1: Altitude simulation	See Table 1	P
	Test cells and batteries shall be stored at a pressure of 11.6kPa or less for at least six hour at ambient temperature (20±5°C)	No leakage, no venting, no disassemble, no rupture and no fire.	P
	Cells and batteries meet this requirement if there is no leakage, no venting, no disassemble, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.		



38.3.4.2	Test 2: Thermal test	See Table 2	P
	<p>Test cells and batteries are to be stored for at least six hours at a test temperature equal to $72\pm 2^{\circ}\text{C}$, followed by storage for at least six hours at a test temperature equal to $-40\pm 2^{\circ}\text{C}$. The maximum time interval between test temperature extremes is 30 minutes. This procedure is to be repeated until 10 total cycles are complete, after which all test cells and batteries are to be stored for 24 hours at ambient temperature ($20 \pm 5^{\circ}\text{C}$). For large cells and batteries the duration of exposure to the test temperature extremes should be at least 12 hours.</p>	<p>No leakage, no venting, no disassemble, no rupture and no fire.</p>	P



Clause	Requirements	Result	Verdict
38.3.4.3	Test 3: Vibration	See Table 3	P
	<p>Cells and batteries are firmly secured to the platform of the vibration machine without distorting the cells in such a manner as to faithfully transmit the vibration. The vibration shall be a sinusoidal waveform with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes. This cycle shall be repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting positions of the cell. One of the directions of vibration must be perpendicular to the terminal face.</p> <p>The logarithmic frequency sweep shall differ for cells and batteries with a gross mass of not more than 12 kg (cells and small batteries), and for batteries with a gross mass of more than 12 kg (large batteries).</p>	No leakage, no venting, no disassemble, no rupture and no fire.	P



	<p>For cells and small batteries: from 7 Hz a peak acceleration of 1gn is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 8gn occurs (approximately 50 Hz). A peak acceleration of 8gn is then maintained until the frequency is increased to 200 Hz.</p> <p>For large batteries: from 7 Hz to a peak acceleration of 1gn is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 2gn occurs (approximately 25 Hz). A peak acceleration of 2gn is then maintained until the frequency is increased to 200 Hz.</p> <p>Cells and batteries meet this requirement if there is no leakage, no venting, no disassemble, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.</p>		
--	--	--	--

38.3.4.4	Test 4: Shock	See Table 4	P
	<p>Test cells and batteries shall be secured to the testing machine by means of a rigid mount which will support all mounting surfaces of each test battery.</p> <p>Each cell shall be subjected to a half-sine shock of peak acceleration of 150gn and pulse duration of 6 milliseconds. Alternatively, large cells may be subjected to a half-sine shock of peak acceleration of 50gn and pulse duration of 11 milliseconds.</p>	No leakage, no venting, no disassemble, no rupture and no fire.	P



38.3.4.5	Test 5: External Short Circuit	See Table 5	P
	<p>The cell or battery to be tested shall be heated for a period of time necessary to reach a homogeneous stabilized temperature of $57 \pm 4^{\circ}\text{C}$, measured on the external case. This period of time depends on the size and design of the cell or battery and should be assessed and documented. If this assessment is not feasible, the exposure time shall be</p>	No disassemble , no rupture and no fire.	P

Battery	Minimum peak acceleration	Pulse duration
Small batteries	<p>150g_n or result of formula</p> $\text{Acceleration (g}_n\text{)} = \sqrt{\left(\frac{100850}{\text{mass}^*}\right)}$ <p>whichever is smaller</p>	6ms
Large batteries	<p>50g_n or result of formula</p> $\text{Acceleration (g}_n\text{)} = \sqrt{\left(\frac{3000}{\text{mass}^*}\right)}$ <p>whichever is smaller</p>	11ms
* Mass is expressed in kilograms.		
<p>Each battery shall be subjected to a half-sine shock of peak acceleration depending on the mass of the battery. The pulse duration shall be 6 milliseconds for small batteries and 11 milliseconds for large batteries. The formulas below are provided to calculate the appropriate minimum peak accelerations.</p> <p>Each cell or battery is subjected to three shocks in the positive direction followed by three shocks in the negative direction of each of three mutually perpendicular mounting positions of the cell for a total of 18 shocks.</p> <p>Cells and batteries meet this requirement if there is no leakage, no venting, no disassemble, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.</p>		



	<p>at least 6 hours for small cells and small batteries, and 12 hours for large cells and large batteries. Then the cell or battery at $57 \pm 4^\circ\text{C}$ shall be subjected to one short circuit condition with a total external resistance of less than 0.1 ohm.</p> <p>This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to $57 \pm 4^\circ\text{C}$, or in the case of the large batteries, has decreased by half of the maximum temperature increase observed during the test and remains below that value. The short circuit and cooling down phases shall be conducted at least at ambient temperature.</p> <p>Cells and batteries meet this requirement if their external temperature does not exceed 170°C and there is no disassemble, no rupture and no fire within six hours of this test.</p>		
--	--	--	--



38.3.4.6	Test 6: Impact / Crush	See Table 6	P
	<p>Impact (applicable to cylindrical cells not less than 18mm in diameter)</p> <p>The test sample cell or component cell is to be placed on a flat smooth surface. A 15.8mm±0.1mm diameter, at least 6cm long, or the longest dimension of the cell, whichever is greater, Type 316 stainless steel bar is to be placed across the centre of the sample. A 9.1 kg ± 0.1kg mass is to be dropped from a height of 61 ± 2.5 cm at the intersection of the bar and sample in a controlled manner using a near friction less, vertical sliding track or channel with minimal drag on the falling mass. The vertical track or channel used to guide the falling mass shall be oriented 90 degrees from the horizontal supporting surface.</p> <p>The test samples is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8mm±0.1mm diameter curved surface lying across the centre of the test samples. Each sample is to be subjected to only a single impact.</p> <p>Cells and component cells meet this requirement if their external temperature does not exceed 170°C and there is no disassemble and no fire during the test and within six hours after this test.</p>	N/A	N/A
	<p>Crush (applicable to prismatic, pouch, coin/button cells and cylindrical cells less than 18mm in diameter)</p> <p>A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1.5cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached.</p> <p>(a) The applied force reaches 13kN±0.78kN; (b) The voltage of the cell drops by at least 100mV; or (c) The cell is deformed by 50% or more of its original thickness.</p>	No disassemble , no rupture and no fire.	P



	<p>Once the maximum pressure has been obtained, the voltage drops by 100mV or more, or the cell is deformed by at least 50% of its original thickness, the pressure shall be released.</p> <p>A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis.</p> <p>Each test cell or component cell is to be subjected to one crush only. The test Samples shall be observed for a further 6 h. The test shall be conducted using test cells or component cells that have not previously been subjected to other tests.</p> <p>Cells and component cells meet this requirement if their external temperature does not exceed 170℃ and there is no disassemble and no fire during the test and within six hours after this test.</p>		
--	--	--	--

38.3.4.7	Test 7: Overcharge	See Table 7	P
	<p>The charge current shall be twice the manufacturer's recommended maximum continuous charge current. The minimum voltage of the test shall be as follows:</p> <p>(a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V.</p> <p>(b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage.</p> <p>(c) Tests are to be conducted at ambient temperature; the duration of the test shall be 24 hours</p>	No disassemble and no fire.	P
	Rechargeable batteries meet this requirement if there is no disassemble and no fire during the test and within seven days after the test.		



38.3.4.8	Test 8: Forced discharge	See Table 8	P
	<p>Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12V D.C. power supply at an initial current equal to the maximum discharge current specified by the manufacturer.</p> <p>The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell shall be forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere).</p> <p>Primary or rechargeable cells meet this requirement if there is no disassemble and no fire during the test and within seven days after the test.</p>	No disassemble and no fire.	P

-----Test Data-----

Table 1	Altitude simulation						P
Sample No.	Mass (kg)		Mass loss (%)	Voltage (V)		Voltage loss (%)	Whether leakage, venting, disassemble, rupture, fire (Y/N)
	Pre-test	After test		Pre-test	After test		
Z1	8.720	8.720	0.002	25.6	25.6	0.000	N
Z2	8.710	8.710	0.003	25.6	25.6	0.000	N
X1	8.720	8.720	0.003	25.6	25.6	0.000	N
X2	8.710	8.710	0.002	25.6	25.6	0.000	N

Table 2	Thermal test						P
Sample No.	Mass (kg)		Mass loss (%)	Voltage (V)		Voltage loss (%)	Whether leakage, venting, disassemble, rupture, fire (Y/N)
	Pre-test	After test		Pre-test	After test		
Z1	8.720	8.718	0.019	25.6	25.0	2.34	N



Z2	8.710	8.708	0.021	25.6	25.0	2.34	N
X1	8.720	8.719	0.017	25.6	25.0	2.34	N
X2	8.710	8.708	0.018	25.6	25.0	2.34	N

Table 3	Vibration						P
Sample No.	Mass (kg)		Mass loss (%)	Voltage (V)		Voltage loss (%)	Whether leakage, venting, disassembly, rupture, fire (Y/N)
	Pre-test	After test		Pre-test	After test		
Z1	8.72	8.72	0.000	25.6	25.4	0.78	N
Z2	8.71	8.71	0.000	25.6	25.4	0.78	N
X1	8.72	8.72	0.000	25.6	25.4	0.78	N
X2	8.71	8.71	0.000	25.6	25.4	0.78	N

Table 4	Shock						P
Sample No.	Mass (kg)		Mass loss (%)	Voltage (V)		Voltage loss (%)	Whether leakage, venting, disassembly, rupture, fire (Y/N)
	Pre-test	After test		Pre-test	After test		
Z1	8.72	8.72	0.000	25.6	25.6	0.00	N
Z2	8.71	8.71	0.000	25.6	25.6	0.00	N
X1	8.72	8.72	0.000	25.6	25.6	0.00	N
X2	8.71	8.71	0.000	25.6	25.6	0.00	N

Table 5	External short circuit	P
Sample No.	Peak temperature (°C)	Whether disassemble, rupture, fire (Y/N)
Z1	57.0	N
Z2	57.0	N
X1	57.0	N
X2	57.0	N



Table 6	Crush	P
Sample No.	Peak temperature (°C)	Whether disassemble, fire (Y/N)
Z3	23.1	N
Z4	24.0	N
Z5	23.8	N
Z6	24.3	N
Z7	23.9	N
X3	22.5	N
X4	23.4	N
X5	23.8	N
X6	23.1	N
X7	24.1	N

Table 7	Overcharge	P
Sample No.	Whether disassemble, fire (Y/N)	
Z8	N	
Z9	N	
X8	N	
X9	N	

Table 8	Forced discharge	P
Sample No.	Whether disassemble, fire (Y/N)	
Z10	N	
Z11	N	
Z12	N	
Z13	N	
Z14	N	
Z15	N	
Z16	N	
Z17	N	
Z18	N	
Z19	N	
X10	N	




Shenzhen BST Technology Co., Ltd.

X11	N
X12	N
X13	N
X14	N
X15	N
X16	N
X17	N
X18	N
X19	N




Procedure Photo





Authenticate the photo on original report only

Sample Photo





Shenzhen BST Technology Co., Ltd.

Statement

This report is invalid without the special seal for report of BST and the signatures of approver.

This report is invalid if is blotted out and deleted.

If the applicant has any questions about results, shall submit to BST within 15 days.

This report is responsible for the sample provided by the client only.

This report shall not be reproduced except in full, or extracted, without the written approval of BST.

The client should provide samples and relevant data, otherwise we will not bear any relevant responsibilities.

The "*" test data bid in this report is commissioned external testing, which is not within the scope of the laboratory's CNAS or CMA authorization, and does not have an impartial effect.

--End of test report--